# FIRMASOFT<sup>™</sup> BATTS: CEILING THERMAL INSULATION FOR RESIDENTIAL CEILING APPLICATIONS

### **Description**

FirmaSoft<sup>™</sup> Batts are made from flexible and resilient glasswool for thermal and acoustic insulation of residential ceilings. FirmaSoft<sup>™</sup> Batts are available in various sizes and densities to fit standard timber spacings.

### Application

FirmaSoft<sup>™</sup> Batts are the trusted choice when it comes to constructing new homes or retrofitting existing buildings for increased thermal efficiency. The FirmaSoft<sup>™</sup> Batts insulation range is available in various thermal R-values and dimensions, ensuring there is an effective and efficient product solution for every application.

FirmaSoft" Batts, renowned for their firmness, are low itch, easy to cut and friction fit standard studs to make homes feel cooler in summer, warmer in winter and provide energy savings all year round.

### **Product Data**

	Material R-value m <sup>2</sup> K/W	Thickness mm	Width mm	Length mm	Batts per pack	m² per pack	Coverage per pack m <sup>2</sup>	Packs per Bale	Product Code
Ceilng	R3.5	175	430	1160	16	8.0	9.0	4	900286
Cei			580	1160	10	6.7	7.6	6	900287
Batts: (	R4.1	105	430	1160	10	5.0	5.6	5	900288
	N4.1	195	580	1160	10	6.7	7.6	6	900289
FirmaSoft <sup>"</sup>	R5.0	215	430	1160	8	4.0	4.5	5	900290
Firr			580	1160	8	5.4	6.1	5	900291

# **Physical Properties**

Property	Test Method/Standard	Result	Unit
Thermal Resistance R-value	AS/NZS 4859.1	Complies	m² K/W
Moisture Absorption	When exposed to environmental conditions of 50°C and 95% relative humidity for four days	< 0.2	% by volume
Maximum Service Temperature	ASTM C411/C447	350	°C
рН	ASTM C871	9 (does not contribute to the corrosion of steel structures)	-



# **Fire Hazard Properties**

FirmaSoft<sup>®</sup> Batts exhibit the following characteristics when tested in accordance with the following standards:

Property	Test Method/Standard	Result
Combustability	AS 1530.1	Non combustible
Early Fire Hazard Indices Ignitability Index Spread of Flame Index Heat Evolved Index Smoked Developed Index	AS/NZS 1530.3	0 0 0 0-1
BAL Compliance	AS 3959	Low-FZ

# Acoustic Performance

### **Sound Absorption**

The performance of sound absorption for insulation is described by the Noise Reduction Coefficient (NRC). In sound absorption application, the NRC is used as an acoustic performance measure. The higher the NRC, the greater the sound absorption at the representative frequencies.

The Noise Reduction Coefficient (NRC) is calculated according to ASTM C423-90A and the average result of four frequencies: 250Hz, 500Hz, 1000Hz, 2000Hz.

FirmaSoft" Batts achieves the following sound absorption results when tested in accordance with AS ISO 354:

			Sound absorption coefficients at frequencies (Hz) of:						
Product	Thickness mm	125	250	500	1000	2000	4000	NRC	αw
FirmaSoft" Batts: Ceiling R3.5	175	0.55	1.0	1.0	1.0	1.0	1.1	0.95	1.0

# **Flow Resistivity**

Acoustic performance of FirmaSoft<sup>®</sup> Batts products used in sound absorption applications can be measured by their resistance to air flow, this is recognised as flow resistivity.

Flow resistivity performance is valuable when evaluating products of the same thickness and density that have varying fibre attributes.

Tested in accordance with ASTM Standard C522-03 Standard Test method for Airflow Resistance of Acoustic Materials. The following table rates the flow resistivity of FirmaSoft<sup>™</sup> Batts products:

Product	Thickness mm	RAYLS/m				
FirmaSoft <sup>™</sup> Batts: Ceiling R2.5	130	2,470				
FirmaSoft <sup>™</sup> Batts: Ceiling R3.0	155	2,850				
FirmaSoft <sup>™</sup> Batts: Ceiling R3.5	175	2,700				
FirmaSoft <sup>™</sup> Batts: Ceiling R4.0	195	3,160				
FirmaSoft <sup>™</sup> Batts: Ceiling R5.0	215	4,500				
FirmaSoft <sup>™</sup> Batts: Ceiling R6.0	250	4,460				

# **Health and Safety**

Fletcher Insulation glasswool products are manufactured from FBS-1 Glasswool Bio-Soluble Insulation<sup>®</sup>. FBS-1 Glasswool Bio-Soluble Insulation<sup>®</sup> is safe to use and is classified as non-hazardous according to the criteria of Safe Work Australia. Fletcher Insulation glasswool insulation can be used with confidence in any residential, commercial or industrial application.

### **Environmental Properties**

Fletcher Insulation avoids the use of Ozone Depleting Potential (ODP) substances in the manufacture or composition of its FBS-1 Glasswool Bio-Soluble Insulation<sup>®</sup>.

The use of these Fletcher Insulation products guarantees the use of Zero ODP insulation while also ensuring that no harmful levels of Volatile Organic Compounds (VOCs) are released. This allows the incorporation of environmentally preferable insulation whilst also maintaining indoor air quality.

### **Technical Specification**

When specifying, state	the following:		
The insulation material	shall be Fletcher Insulation	FirmaSoft <sup>™</sup> Batts: Ceiling	g Rm² K/W
(Material R-value)	(thickness) x	(width) x	(length) mm.

© Fletcher Insulation Pty Limited 2019. Fletcher Insulation reserves the right to change product specifications without prior notification. Information in this publication and otherwise supplied to users as to the subject product is based on our general experience and is given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or is to be implied with respect to either such information or the product itself, in particular the suitability of the product for any particular purpose. The purchaser should independently determine the suitability of the product for the intended application. Unless otherwise stated those trade marks followed by ® are registered trade marks of Fletcher Insulation Pty Ltd ACN 001 175 355, a member of the Fletcher Building Group. RTDS11\_Revision\_0\_Isue Date 06102020.

